

## C9 氢化石油树脂/C9 Hydrogenated Hydrocarbon Resin RES-900

### 1. 产品描述/Product Description

碳九氢化石油树脂是由乙烯裂解副产 C9 馏分通过聚合及加氢获得的水白色热塑性树脂。具有较好的热稳定性，以及与 SIS、EVA、SBS、SEBS、聚烯烃等聚合物有良好的相容性，可用于橡胶混炼。

RES-900 is water-white thermoplastic resin obtained from polymerizing of Aromatic and hydrogenation. With the good heat resistance and good compatibility with polymer such as SIS, EVA, SBS, SEBS, polyolefin, etc., HR-100 is widely used for rubber mixing.

### 2. 典型性能/Typical properties

序号 No.	项目 Item	参数 Parameter	标准 Standard
1	软化点 (环球法, °C) Softening Point (Ring & Ball, °C)	100	ASTM E 28
2	颜色 Color	< 1	Gardner
3	黄度指数 Yellow Index	< 4.5	ASTM D 1925

### 3. 包装/Packaging

- 包装容器：聚乙烯袋/牛皮纸袋  
Package: Polyethylene bags/ Kraft paper bags
- 包装规格：500-700kg/袋或 25kg/袋  
Weight: 500-700kg/bag or 25kg/bag

### 4. 储存/Storage

本品应室内储存，注意防火、防晒、防雨、放手钩，且环境温度不超过 35°C，相对湿度不大于 85%。

This product should be stored indoor, and pay attention to fire prevention, sun protection and rain protection. The room temperature must not higher than 35°C, and the humidity must not higher than 85%.